

USSN: 09/838,884

Attorney Docket No.: 117-P-1345US11

Amendments to the Claims

A detailed list of all claims under examination is set out below. Please amend claim 34 as shown below in marked form:

1. (withdrawn): A coated substrate comprising a strippable intermediate coating atop the substrate and a strip agent-permeable waterborne overcoat adhered to the intermediate coating, wherein the dried overcoat is less strippable and more wear-resistant than the dried intermediate coating.
2. (withdrawn): A coated substrate according to claim 1, wherein the substrate comprises a floor.
3. (withdrawn): A coated substrate according to claim 2, wherein the substrate comprises a resilient flooring material.
4. (withdrawn): A coated substrate according to claim 3, wherein the substrate comprises a vinyl or vinyl composite tile.
5. (withdrawn): A coated substrate according to claim 1, wherein the substrate comprises a wall, ceiling, label, emblem, sign or vehicle.
6. (withdrawn): A coated substrate according to claim 1, wherein the intermediate coating comprises a metal-catalyzed acrylic.
7. (withdrawn): A coated substrate according to claim 1, wherein the intermediate coating has a strippability rating of 6 or more on a 7 point scale, corresponding to at least partial strip with softened coating in all areas, using a test strip agent made using a 25% water solution of a concentrate that contained 59% softened water, 6% sodium xylene sulfonate, 4.5% potassium hydroxide, 10% monoethanolamine, 0.2% tetrasodium EDTA, 10% ethylene glycol phenyl ether and 0.05% fluorosurfactant, and a 10 minute standing time.
8. (withdrawn): A coated substrate according to claim 1, wherein the intermediate coating has a thickness of about 2.5 to about 75 micrometers.

BEST AVAILABLE COPY

USSN: 09/838,884Attorney Docket No.: 117-P-1345US11

9. (withdrawn): A coated substrate according to claim 1, wherein the overcoat comprises an emulsion, suspension or dispersion.
10. (withdrawn): A coated substrate according to claim 1, wherein the overcoat is radiation curable.
11. (withdrawn): A coated substrate according to claim 1, wherein the overcoat is UV-curable.
12. (withdrawn): A coated substrate according to claim 1, wherein the overcoat comprises an acrylate, urethane or acrylated urethane.
13. (withdrawn): A coated substrate according to claim 12, wherein the overcoat comprises an aromatic urethane.
14. (withdrawn): A coated substrate according to claim 12, wherein the overcoat comprises an aliphatic polyester urethane.
15. (withdrawn): A coated substrate according to claim 1, wherein the overcoat is not metal crosslinked.
16. (withdrawn): A coated substrate according to claim 1, wherein the dried overcoat has a strippability rating of 4 or less on a 7 point scale, corresponding to no more than severe chemical attack on the overcoat and the onset of stripping, using a test strip agent made using a 25% water solution of a concentrate that contained 59% softened water, 6% sodium xylene sulfonate, 4.5% potassium hydroxide, 10% monoethanolamine, 0.2% tetrasodium EDTA, 10% ethylene glycol phenyl ether and 0.05% fluorosurfactant, and a 30 minute standing time.
17. (withdrawn): A coated substrate according to claim 1, wherein the dried overcoat has a thickness of about 2.5 to about 75 micrometers.
18. (withdrawn): A coated substrate according to claim 1, wherein the overcoat comprises two or more different layers of materials.
19. (withdrawn): A coated substrate according to claim 1, wherein the substrate comprises a floor and the overcoat is UV curable.

USSN: 09/838,884

Attorney Docket No.: 117-P-1345US11

20. (withdrawn): A strippable laminate finish kit, comprising one or more containers of a strippable intermediate coating and a strip agent-permeable waterborne overcoat, wherein the dried overcoat adheres to the intermediate coating and is less strippable and more wear resistant than the dried intermediate coating.
21. (withdrawn): A strippable laminate finish kit according to claim 20, further comprising a strip agent.
22. (withdrawn): A strippable laminate finish kit according to claim 20, wherein the overcoat comprises a one-part photopolymerizable material.
23. (withdrawn): A strippable laminate finish kit according to claim 20, wherein the overcoat comprises a UV curable material.
24. (withdrawn): A strippable laminate finish kit according to claim 20, wherein the overcoat comprises an acrylate, urethane or acrylated urethane.
25. (withdrawn): A strippable laminate finish kit according to claim 20, wherein the overcoat comprises an aromatic urethane.
26. (withdrawn): A strippable laminate finish kit according to claim 20, wherein the overcoat comprises an aliphatic polyester urethane.
27. (withdrawn): A strippable laminate finish kit according to claim 20, wherein:
- a) the intermediate coating has a strippability rating of 6 or more on a 7 point scale, corresponding to at least partial strip with softened coating in all areas, and
 - b) the overcoat has a strippability rating of 4 or less on a 7 point scale, corresponding to no more than severe chemical attack on the overcoat and the onset of stripping, using a test strip agent made using a 25% water solution of a concentrate that contained 59% softened water, 6% sodium xylene sulfonate, 4.5% potassium hydroxide, 10% monoethanolamine, 0.2% tetrasodium EDTA, 10% ethylene glycol phenyl ether and 0.05% fluorosurfactant, and a 10 minute standing time.
28. (original): A method for applying a finish to a substrate, comprising:

USSN: 09/838,884

Attorney Docket No.: 117-P-1345US11

- a) applying to the substrate a strippable intermediate coating;
 - b) drying the intermediate coating; and
 - c) applying a strip agent-permeable waterborne overcoat to the intermediate coating;
- wherein the dried overcoat adheres to the intermediate coating and is less strippable and more wear resistant than the intermediate coating.
29. (original): A method according to claim 28, wherein the overcoat comprises an emulsion, suspension or dispersion.
30. (original): A method according to claim 28, wherein the overcoat comprises an acrylate, urethane or acrylated urethane.
31. (original): A method according to claim 28, wherein the overcoat is UV curable.
32. (original): A method according to claim 31, wherein the overcoat is applied in two or more coats each of which is UV cured before application of any further coat.
33. (original): A method for removing a multilayer finish, comprising:
- a) applying a strip agent to a dried waterborne radiation cured overcoat adhered to a dried intermediate layer atop a substrate;
 - b) allowing the strip agent to permeate through the overcoat to attack the intermediate layer; and
 - c) removing the intermediate layer and overcoat without removing substantial portions of the underlying substrate.
34. (currently amended): A method according to claim 33, wherein permeation of the strip agent through the overcoat is enhanced by a ~~by~~ mechanically roughening the overcoat prior to applying the strip agent.
35. (original): A method according to claim 33, wherein removal of the intermediate layer and overcoat occurs in less than 10 minutes after application of the strip agent.

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.